



303




309



310



349



325



332



331



321

MIRAGE

IT

Composizione

100% PL FR (Tr Cs)

Peso

gr./m²-gr./mtl. 330 ± 10% - 460 ± 10%

Altezza

m. 55 ± 5% 1,40 ± 2%

Resistenza all'abrasione

UNI EN ISO 12947 Cicli 100.000 ± 20%

Resistenza alla luce

SO 105-B02 (Xenotest)

Resistenza allo sfregamento

ISO 105-X12 (Crockmeter)

Pilling

ISO 12945-2 grado 1-5 4/5 ± ½

RESISTENZA AL FUOCO

EN ISO 6940/6941:

BS 5852 CRIB N°5 USING A CM FOAM 35 KG/CU.M.

B1 DIN 4102

EN 1021 PART 1-2 USING A CM FOAM 35 KG/CU.M.

EN 13773 BURNING BEHAVIOUR: CLASS 1

EN 13501-1 ESP 1,2 : B-S1, D0

CALIF.BULL.117 JUNE 2013

FIRE PROTECTION CLASSIFICATION: 5.3

M1 + NF D 60-013:2006 AM18

FAR.25853 CLASSIFICATION: YES

B1 - OENORM 3800 PART 1 + OENORM B3825

AZIMUT

MED/3.19 MED/3.21: DRAPERIES, CURTAIS AND BEDDING COMP.

MED ANNEX A.1 ITEM:A.1/3.20 UPHOLSTERED FURNITURE

EN

Composition

100% PL FR (Tr Cs)

Weight

gr./m²-gr./mtl. 330 ± 10% - 460 ± 10%

Width

m. 55 ± 5% 1,40 ± 2%

Abrasion resistance

UNI EN ISO 12947 Cicli 100.000 ± 20%

Light fastness

SO 105-B02 (Xenotest)

Fastness to rubbing

ISO 105-X12 (Crockmeter)

Pilling

ISO 12945-2 grado 1-5 4/5 ± ½

FIRE RESISTANCE

EN ISO 6940/6941:

BS 5852 CRIB N°5 USING A CM FOAM 35 KG/CU.M.

B1 DIN 4102

EN 1021 PART 1-2 USING A CM FOAM 35 KG/CU.M.

EN 13773 BURNING BEHAVIOUR: CLASS 1

EN 13501-1 ESP 1,2 : B-S1, D0

CALIF.BULL.117 JUNE 2013

FIRE PROTECTION CLASSIFICATION: 5.3

M1 + NF D 60-013:2006 AM18

FAR.25853 CLASSIFICATION: YES

B1 - OENORM 3800 PART 1 + OENORM B3825

AZIMUT

MED/3.19 MED/3.21: DRAPERIES, CURTAIS AND BEDDING COMP.

MED ANNEX A.1 ITEM:A.1/3.20 UPHOLSTERED FURNITURE

